

02 Wood Tex Classic

Flügger Wood Tex Classic is oil-based products for exterior wood with good penetration and maximum protection against moisture and water. The products can be used at low temperatures.

Product properties

Pigmented priming paint that penetrates and provides extra durability, hiding power and protection against moisture. Inhibits mould and mildew growth on the surface of the final treatment.

- Opaque priming paint
- Protects against moisture
- Extra durability



Product use

Intermediate treatment of primed wood before finishing with opaque wood stain or paint. The substrate must be primed or previously treated.

Substrate

Must be clean, dry, solid and suitable for paint treatment.

Insufficiently protected cross-cut wood, water traps or the risk of water accumulation must not occur.

The moisture level in the wood prior to paint treatment max.:

Windows and doors: 12% ± 3; Overhangs, fences and cladding: 18%.

Treatment

Loose wood stain, paint and decayed wood fibres must be removed by sanding and cleaning

Dirt, grease, chalking material and algae, mould and mildew must be removed by cleaning.

Round off sharp edges for best possible hiding power

All bare woodwork must be treated before or immediately after mounting

Glossy, previously painted surfaces must be sanded matt.

New or bare cleaned wood must be primed with Flügger 01 Wood Tex Classic Priming Oil.

Substrate which has stood untreated for longer than 4 weeks must be cleaned and loose wood fibres removed

Application

Brush or roller.

If applying using a roller, brush over afterwards.

Choose appropriate tools for the desired finish.

Apply wet-on-wet, and finish by brushing in the same direction.

Cold or heat can affect the material's viscosity

Condensation must not form.

Avoid working in direct sunlight.

Cold weather and high atmospheric humidity increase the drying time, complete curing and re-treatment interval.

High temperature and low atmospheric humidity reduce the drying time and complete curing.

Always apply test treatments to check and accept the adhesion and results.

Expected result

Mat and opaque.
Finish treatment with opaque wood stain or paint.

Please note!

Protect freshly painted surface from adverse weather conditions.
Take appropriate measures against the effects of moisture and rainfall on freshly painted surfaces.
The surface achieves maximum robustness when fully cured.

Environmental information

Clean off the paint from tools and wash them with white spirit. Bring remains of fluent paint to the local recycling centre.
Minimize your paint waste by pre-estimating how much paint you need. Keep the leftover paint for future use so you can effectively reduce the environmental impact.

Storage: Cool, frost free and tightly closed

Technical Data

Product Type	Priming paint
Density (kgs/l)	1.31
Solids Weight %	63
Solids Vol. %	44
Nominal spreading rate (m ² /ltr.)	8
Long spreading rate (m ² /l)	10
Short Spreading rate (m ² /l)	6
Min. working temp. during application and drying/curing	Min. +5°C
Humidity	Max. humidity 80 % RH.
Drying time at 20° C, 60 % RH (Hours)	17
Recoatable at 20° C, 60 % RH (Hours)	24
Fully cured at 20° C, 60 % RH (Days)	28
Dilution	Do not dilute
Cleaning of Tools etc.	White spirit

Current TDS Version

February 2023

Replaces TDS Version

February 2022